

CLAIMS

- sub  
B1
- 5 1. Ophthalmic lens consisting of a substrate made of organic glass, of an abrasion-resistant coating, of a layer of impact-resistant primer and of an inorganic anti-reflective coating, characterized in that the surface of the said substrate is covered with the abrasion-resistant coating and in that the impact-resistant primer layer is inserted between the said abrasion-resistant layer and the anti-reflective coating.
- 10 2. Lens according to claim 1, wherein the substrate is chosen from:
- (I) the glasses obtained by polymerization of diethylene glycol bis(allyl carbonate);
  - (II) the glasses obtained by polymerization of acrylic monomers derived from bisphenol A;
  - 15 (III) the glasses obtained by polymerization of allyl monomers derived from bisphenol A.
3. Lens according to claim 1, wherein the substrate is chosen from:
- 20 (A) the glasses obtained from poly(methyl methacrylate);
  - (B) the glasses obtained from polystyrene resin;
  - (C) the glasses made of resin based on diallyl phthalate.
4. Lens according to claim 1, wherein the impact-resistant interlayer has an intrinsic Bayer value lower than or equal to 2, at a thickness of 3  $\mu\text{m}$ .
- 25 5. Lens according to claim 1, wherein the impact-resistant primer is a thermoplastic or heat-curable polymer composition which has a solids content ranging from 5 to 20% by weight relative to the total weight of the primer composition.
- 30 6. Lens according to claim 1, wherein the thickness of the impact-resistant interlayer in the cured state is between 0.2 and 1  $\mu\text{m}$ .
7. Lens according to claim 1, wherein the composition of the impact-resistant primer consists of a thermoplastic polyurethane resin obtained by reaction of a diisocyanate with a compound comprising a reactive hydrogen at each end.

8. Lens according to claim 1, wherein the composition of the impact-resistant primer consists of a heat-curable polyurethane resin obtained by reaction of a blocked polyisocyanate and of a polyol.

9. Lens according to claim 1, wherein the composition of the impact-resistant primer consists of a copolymer of acrylic and/or methacrylic monomers and of aromatic vinyl compounds.

10. Lens according to claim 1, wherein the composition of the impact-resistant primer consists of a polysiloxane.

11. Lens according to claim 10, wherein the composition of the impact-resistant primer contains, in a solvent medium, one or a number of silane hydrolysate(s) with an epoxy group containing at least one Si-alkyl group and containing no fillers.

12. Lens according to claim 1, wherein the hard abrasion-resistant coating is obtained by curing a composition containing:

a) colloidal silica which has a mean particle diameter of between 1 and 100  $\mu\text{m}$ ;

b) a solvent;

c) a hydrolysate or a mixture of hydrolysates of silane compound(s) of formula:



in which:

$\text{R}^1$  denotes an organic group containing an epoxy group;

$\text{R}^2$  is a hydrocarbon radical which has 1 or 2 carbon atoms;

$\text{R}^3$  is a hydrocarbon group which has from 1 to 4 carbon atoms, and  $\text{a}$  is 0 or 1 in value.

13. Lens according to claim 1, wherein the thickness of the abrasion-resistant layer, in the cured state, is between 1 and 15  $\mu\text{m}$ .

14. Lens according to claim 12, wherein the composition of the abrasive-resistant coating has a colloidal silica content of between 0 and 40% by weight in the solids content.

113  
B2

15. Lens according to claim 1, wherein the anti-reflective coating consists of a mono- or multilayer film based on dielectric materials and deposited by vacuum deposition.

16. Lens according to claim 1, successively including :

5 a) a substrate made of glass obtained by polymerization of diethylene glycol bis(allyl carbonate);

b) a hard abrasion-resistant coating obtained by curing a composition containing, in methanol, colloidal silica and a hydrolysate of  $\gamma$ -glycidyloxypropylmethyldiethoxysilane;

10 c) an impact-resistant interlayer obtained by curing a composition containing, in methanol, a hydrolysate of  $\gamma$ -glycidyloxypropylmethyldiethoxysilane or of  $\gamma$ -glycidyloxypropyl-trimethoxysilane;

d) a multilayer anti-reflective coating.

15 17. Lens according to claim 1, successively including :

a) a substrate made of glass obtained by polymerization of diethylene glycol bis (allyl carbonate);

20 b) an abrasion-resistant coating obtained by curing a composition containing, in methanol, colloidal silica and a hydrolysate of  $\gamma$ -glycidyloxypropylmethyldiethoxysilane;

c) an impact-resistant interlayer obtained by (35) curing a composition containing 4,4'-dicyclohexylmethane diisocyanate and polyethylene glycol;

d) a multilayer anti-reflective coating.

25 18. Process for the manufacture of an ophthalmic lens as defined in claim 1, comprising :

- applying the abrasion-resistant coating onto the surface of the organic glass substrate,
- depositing the layer of impact-resistant primer is deposited onto the abrasion-resistant layer ; and
- 30 - depositing the anti-reflective coating is onto the impact-resistant primer.

19. Process according to claim 18, wherein the abrasion-resistant layer and the layer of impact-resistant primer are deposited by

13  
 14  
 15  
 16  
 17  
 18  
 19  
 20  
 21  
 22  
 23  
 24  
 25  
 26  
 27  
 28  
 29  
 30  
 31  
 32  
 33  
 34  
 35  
 36  
 37  
 38  
 39  
 40  
 41  
 42  
 43  
 44  
 45  
 46  
 47  
 48  
 49  
 50

centrifuging, by dipping or by spraying and in that the anti-reflective coating is applied by vacuum deposition or sol-gel deposition.

20. Process according to claim 18, wherein the abrasion-resistant and impact-resistant primer layers are pretreated using a surface  
5 activation treatment by a chemical or physical route.

21. Process according to claim 20, wherein the surface activation treatment is an alkaline chemical etching, an oxygen plasma treatment or an ion bombardment in a vacuum vessel.

ADD B47

11/03/2004 14:00:00